

## (12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)


(19) World Intellectual Property Organization  
International Bureau(43) International Publication Date  
4 September 2003 (04.09.2003)

PCT

(10) International Publication Number  
WO 03/072206 A2

- (51) International Patent Classification<sup>7</sup>: A63C
- (21) International Application Number: PCT/US03/05518
- (22) International Filing Date: 20 February 2003 (20.02.2003)
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data:  
60/358,988 21 February 2002 (21.02.2002) US
- (71) Applicant (for all designated States except US): NITINOL TECHNOLOGIES, INC. [US/US]; P.O. Box 1561, Milton, WA 98354 (US).
- (81) Designated States (national): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, OM, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.
- (84) Designated States (regional): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, SE, SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).
- (72) Inventor; and
- (75) Inventor/Applicant (for US only): JULIEN, Gerald, J. [US/US]; 11812 21st Street East, Puyallup, WA 98372 (US).
- (74) Agent: NEARY, J., Michael; Neary Law Office, 542 SW 298th Street, Federal Way, WA 98023 (US).
- Published:  
— without international search report and to be republished upon receipt of that report
- For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: NITINOL ICE BLADES



(57) Abstract: A Nitinol ice blade includes a blade body having attachment structure by which it is held in a blade holder of an ice travel device, such as an ice skate or ice boat. The processes and products made by the processes. The processes include selecting a Type 60 Nitinol sheet or bar that has been hot-worked at a temperature of above about 900 °C to a reduction of at least 2% in the dimension of said hot-working. Blade blanks are cut from the sheet, and the blade blanks are heated to between 600°C to about 800°C and immediately quenched to ambient temperature to produce blanks having a hardness of about 48-53RC. The running edge of the blade blanks a ground to a desired profile and sharpness. The ground blades may then be heated to an elevated temperature of about 850-1000°C and immediately quenched to produce a hardness at the edge of above 56RC.